

## **GLAZED PORCELAIN TILES**

## **DESIGN QUALIFYING REPORT**

DIGITAL PRINTING RUSTIC MATT COLLECTION (SLATE)

**SIZE** 600X600 **CODE** & **NAME**  95M.MA **96M.MA 97M.MA**  **GEO SLATE PALE WHITE GEO SLATE NATURAL** GEO SLATE PALE NERO

# **FEATURES**

Natural slate with a wide range of colours in a structured surface, imitating the beauty of natural slate with value

	DEMENTION & SURFACE QUALITY						
		Description of the Test	Test Method	International Specification	Royal Porcelain Value		
	↑ <b></b>	Length & Width (Average)	ISO 10545.2	Set by Manufacture	600 mmX600 mm (Squared)		
1	ļ l	Deviation in Length & Width	ISO 10545.2	± 0.6 %	Max ± 0.10 %		
2		Thickness (Average)	ISO 10545.2	Set by Manufacture	8.6 mm		
2	1	Deviation in Thickness	ISO 10545.2	± 10 %	Max ± 2.0 %		
3	$\overline{0}$	Straightness of Sides	ISO 10545.2	± 0.5 % (Max 2 mm)	0.2 % (Max) (1.0 mm)		
4	Ů	Rectangularity	ISO 10545.2	± 0.6 % (Max 4 mm)	Rectified (Diagonal ±0.3mm)		
5	<b>&gt;</b> −€	Surface Flatness	ISO 10545.2	± 0.5 % (Max 2 mm)	0.3 % (Max) (1.8 mm)		
6	•:	Surface Quality	ISO 10545.2	Min 95 %	Min 95 %		
		I	PHYSICAL PROPER	TIES			
7	<b>%</b> .	Water Absorption by mass (Average)	ISO 10545.3	< 0.5 %	0.2 % (Max 0.3 %)		
3	<b>★</b>	Modulus of Rupture	ISO 10545.4	> 35 N/mm <sup>2</sup>	> 38.0 N/mm <sup>2</sup>		
9	<u> </u>	Abrasive Resistance (Maximum)	ISO 10545.7	Set by Manufacture	Class IV (3000 revolutions)		
.0	*	Moh's Scale Hardness	EN 101	Set by Manufacture	7.0 – 7.5		
.1	Î	Density	ISO 10545.3	> 2.0 g/cc	2.4 g/c		
2	*	Colour Resistance to light	ISO 10545.16	Resistance	Resistance		
		1	THERMAL PROPER	TIES			
.3	$\overline{\longleftrightarrow}$	Thermal Expansion	ISO 10545.8	$< 90.0 \text{ X } 10^{-7}  ^{\circ}\text{C}^{-1}$	74.0 X 10 <sup>-7</sup> °C <sup>-1</sup>		
4	<b>6</b>	Moisture Expansion	ISO 10545.10	Nil	Nil		
.5	***	Resistance to Thermal Shock	ISO 10545.9	Min 10 Cycle	Resistant		
.6	}	Resistance to Crazing	ISO 10545.11	Min 4 Cycle	Resistant		
7	鱳	Frost Resistance	ISO 10545.12	Resistance	Resistant		
		C	CHEMICAL PROPER	RTIES			
.8	I.R.	Chemical Resistance	ISO 10545.13	Resistant	Resistant		
9	S	Resistance to Stains	ISO 10545.14	Min Class III	Class V		

Display of Tiles

At least 4 tiles should be properly displayed to express random effect  $\,$ 

### APPLICATIONS

Product features are with high abrasion resistance and high scratch hardness. As such, it is indicated for flooring semi public commercial areas (shops, hotels etc) as well as for domestic use (living room, corridors, veranda, car porch etc). Also it is suitable for wet areas (open veranda etc) since the matt surface is less slippery.

Prepared by:-	Manager - QA, R &D	Date	20-Feb-12
Revision No.	3	Date of Revision	1-May-17