FULLY VITRIFIED HOMOGENEOUS PORCELAI	Ν

## DESIGN QUALIFYING REPORT

HOMOGENEOUS SOLID-POLISHED COLLECTION



			I	1	Γ	_	
Size Code		Finish	Name Solid - Ivory				
	600X300 RC.001.000107.PL.0M 600X300 RC.001.000112.PL.0M		Polished Polished	Solid - Off			
	600X300 RC.001.000112.PL.0M		Polished	Solid - Dar			
				FEATURES			
			DIN	IENSION & SURFACE QUA	LITY		
		De	escription of the Test	Test Method	International Specification	Royal Ceramics Value	
1		Length & Width (Average)		ISO 10545.2	Set by Manufacturer	R(600X300mm)	
		Deviation in Length & Width		ISO 10545.2	± 0.3 %	±0.2mm	
2		Thickness (Average)		ISO 10545.2	Set by Manufacturer	9.0mm	
r		Deviation in Thickness		ISO 10545.2	± 5 %	±0.3mm	
3		Straightness of Sid	es	ISO 10545.2	± 0.5 % (Max 2 mm)	±0.8mm	
4		Rectangularity		ISO 10545.2	± 0.6 % (Max 4 mm)	±1.5mm (With respect to the 600mm side) ±0.9mm (With respect to the 300mm side)	
5	>-€	Surface Flatness		ISO 10545.2	± 1.8 mm (Max)	±1.6mm	
6	•:	Surface Quality		ISO 10545.2	Min 95 %	Min 95 %	
		I.		PHYSICAL PROPERTIES			
7		Water Absorption	by mass (Average)	ISO 10545.3	< 0.5 %	Maximum < 0.5 %	
8	*	Modulus of Rupture		ISO 10545.4	> 35 N/mm2	Minimum > 35 N/mm2	
9		Abrasion Resistance (Maximum)-Deep Abrasion		ISO 10545.6	Maximum 175mm3	Maximum < 165mm3	
10		Moh's Scale Hardness		EN 101	Set by Manufacturer	N/A	
11	K	Slipperiness		ISO 10545.17	Set by Manufacturer	N/A	
12	*	Colour Resistance to light		ISO 10545.16	Resistant	Resistant	
				THERMAL PROPERTIES	1	-	
13	$\overleftarrow{\longleftrightarrow}$	Thermal Expansion		ISO 10545.8	< 90.0 X 10-7 °C-1	< 65.0 X10-7°C-1	
14		Moisture Expansion		ISO 10545.10	Nil	N/D	
15	Contraction of the second	Resistance to Thermal Shock		ISO 10545.9	Min 10 Cycle	Resistant	
16	Ż	Resistance to Crazi	ing	ISO 10545.11	Min 4 Cycle	N/A	
17	鱳	Frost Resistance		ISO 10545.12	Resistant	N/A	
				CHEMICAL PROPERTIES	Γ	1	
18		Chemical Resistand	ce	ISO 10545.13	Resistant	Resistant	
19	*	Resistance to Stain	15	ISO 10545.14	Manufactuter is to state classification	Class II	
			RAN	DOMNESS & DISPLAY OF	TILES		
20	20 Image: Display of Tiles   At least 4 tiles should be properly displayed.						
Pro	oduct is	Fully Vitrified Home	ogeneous porcelain with <b>low scratch h</b> with fr	APPLICATIONS ardness. It is recommended esh water and household che		g and maintenance can be done	
			(	Certifications of Conformit	у		
	ISO 9001, ISO 13006, ISO 14001, ISO 45001						
			Eng.Production	Date:	24/10/2023		
Prepared by: Eng.Production Date: 24/10/2023							

Revision No.	Manager - QA and R & D	Date of Revision:	12/11/2024
--------------	------------------------	-------------------	------------