FULLY VITRIFIED HOMOGENEOUS PORCELAIN

DESIGN QUALIFYING REPORT

HOMOGENEOUS SOLID-POLISHED COLLECTION



		Size	Code	Finish	Name	e	
	6	00X1200	RC.001.000107.PL.0U	Polished		Name Solid - Ivory	
			RC.001.000103.PL.0U	Polished	Solid - Brilliant White		
		600X1200 RC.001.000103.PL.00		Polished	Solid - Pearl		
	6	600X1200 RC.001.000611.PL.0U		Polished	Solid - Anthracite		
	600X1200 RC.001.000654.PL.0U			Polished	Solid - Ash		
	600X1200 RC.001.000451.PL.0U			Polished	Solid - Walnut		
	600X1200 RC.001.000227.PL.0U			Polished	Solid - Cream		
600X1200 RC.001.000159.PL.0U			RC.001.000159.PL.0U	Polished	Solid - Smoke		
600X1200 RC.001.000257.PL.0U				Polished	Solid - Sand		
	600X1200 RC.001.000256.PL.0U			Polished	Solid - Rose Solid - Charcoal		
	0	00X1200	RC.001.000614.PL.0U	Polished	Solid - Cha	ircoal	
1		Da	scription of the Test	MENSION & SURFACE QUA		Powel Coromics Valu	
_				Test Method	International Specification	Royal Ceramics Valu	
	$\begin{bmatrix} \uparrow & \\ \uparrow & \\ \uparrow & \\ \hline \\ \hline$	Length & Width (Average)		ISO 10545.2	Set by Manufacturer	R(600X1200mm)	
		Deviation in Length & Width		ISO 10545.2	± 0.3 %	±0.2mm	
		Thickness (Average)		ISO 10545.2	Set by Manufacturer	9.0mm	
	A	Deviation in Thickness		ISO 10545.2	± 5 %	±0.3mm	
		Straightness of Side	25	ISO 10545.2	± 0.5 % (Max 2 mm)	±0.8mm	
	90. •20	Rectangularity		ISO 10545.2	± 0.6 % (Max 4 mm)	±1.5mm	
	-	Surface Flatness		ISO 10545.2	± 1.8 mm (Max)	±1.6mm	
	•:	Surface Quality		ISO 10545.2	Min 95 %	Min 95 %	
-				PHYSICAL PROPERTIES	ł	<u>.</u>	
	***	Water Absorption	oy mass (Average)	ISO 10545.3	< 0.5 %	Maximum < 0.5 %	
	*	Modulus of Rupture		ISO 10545.4	> 35 N/mm2	Minimum > 35 N/mm	
		Abrasion Resistance (Maximum)-Deep Abrasion		ISO 10545.6	Maximum 175mm3	Maximum < 165mm3	
)		Moh's Scale Hardn	ess	EN 101	Set by Manufacture	N/A	
L	×	Slipperiness		ISO 10545.17	Set by Manufacture	N/A	
2	**	Colour Resistance t	o light	ISO 10545.16	Resistant	Resistant	
				THERMAL PROPERTIES	1		
3		Thermal Expansion		ISO 10545.8	< 90.0 X 10-7 °C-1	< 65.0 X10-7°C-1	
ł		Moisture Expansion		ISO 10545.10	Nil	N/D	
5	S. S. S.	Resistance to Thermal Shock		ISO 10545.9	Min 10 Cycle	Resistant	
5	¥	Resistance to Crazing		ISO 10545.11	Min 4 Cycle	N/A	
7	鱳	Frost Resistance		ISO 10545.12	Resistant	N/A	
				CHEMICAL PROPERTIES			
8		Chemical Resistanc	e	ISO 10545.13	Resistant	Resistant	
9	*	Resistance to Stain	s	ISO 10545.14	Manufacturer is to state classification	Class II	
			RA	NDOMNESS & DISPLAY OF	TILES		
0		Display of Tiles At least 4 tiles should be properly displayed.					

Product is a Fully Vitrified Homogeneous porcelain tile with low scratch hardness . It is recommended to apply in low traffic areas . Cleaning and maintenance can be done with fresh water and household chemicals. Certifications of Conformity						
Prepared by:	Eng.Production	Date:	11/11/2023			
Revision No.	Manager - QA and R & D	Date of Revision:	12/11/2024			