Ro	cell.	Sizo	QUALIFYING REPORT 60cm x 30cm	
OYAL CER	AMICS LANKA LTD	Size		
IDENTIFICATION NAME			TECHNO QUARTZ	
Product Category			FULLY VITRIFIED FULL BODY PORCELAIN (RUSTIC)	
	RC.0SC.0007G4.AM.0M		TECHNO QUARTZ - WHITE	
		RC.0SC.0007G5.AM.0M	TECHNO QUARTZ - BROWN	
RC.0		RC.0SC.0007G6.AM.0M	TECHNO QUARTZ - LIGHT GREEN TECHNO QUARTZ - LIGHT GREEN TECHNO QUARTZ - PLACK	
		RC.0SC.0007G7.AM.0M		
	RC.0SC.0007G9.AM.0M		TECHNO QUARTZ - BLACK FEATURES	
S	atin Matt surfac		g a Soft range of colou is given by random c	rs with stone effect. The elegance of the lecorations
	Description of the Test		Test Method	
1	Length & Width	(Average)	ISO 10545.2	R(600 x 300 mm)
2	Rectangularity (A	Average)	ISO 10545.2	Rectified (Diagonal ±0.3 mm)
3	Thickness (Average)		ISO 10545.2	10.0 ± 0.2 mm
4	Surface Flatness (Average)			
	Centre Curvature related to the diagonal calculated from work size		ISO 10545.2	±0.2 % (±0.9 mm,±1.4 mm)
	Edge Curvature related to the corresponding work size		ISO 10545.2	±0.3 % (±0.9 mm,±1.4 mm)
	Warpage related to the diagonal calculated from the work size		ISO 10545.2	±0.3 % (±0.9 mm,±1.4 mm)
5	Water Absorption by mass (Average)		ISO 10545.3	less than 0.5%
6	Modulus of Rupture (Minimum)		ISO 10545.4	35.0 N/mm ²
7	Deep abrasion		ISO 10545.6	165 mm ³
8	Surface abrasion (Minimum)		ISO 10545.7	Class III (>750revolution)
9	Resistance to Thermal Shock		ISO 10545.9	Resistant
10	Resistance to Crazing		ISO 10545.11	Resistant
11	Chemical Resistance		ISO 10545.13	Resistant
12	Resistance to Stains		ISO 10545.14	Class V
13	Moh's Scale Hardness			7
14	Display of Tiles			At least 6 tiles should be properly displayed express random effect
	1		APPLICATIONS	1
Proc			igh scratch hardness	. It is suitable for flooring in medium traf water and household chemicals
	Prepared by:	Eng. Prod.	Date	11-02-2008
	Reviewed by: Revision No.	Manager - QA, R &D 3	Date Date of Revision	11-02-2008 22-09-2018