



GLAZED PORCELAIN TILES

DESIGN QUALIFYING REPORT

DIGITAL PRINTING SATIN MATT COLLECTION

SIZE 600X1200	CODE & NAME	7LG.SM	MEGAN BLACK
--------------------------------	------------------------	---------------	--------------------

FEATURES

DEMENTION & SURFACE QUALITY

	Description of the Test	Test Method	International Specification	Royal Porcelain Value
1	Length & Width (Average)	ISO 10545.2	Set by Manufacture	600 mmX1200 mm (Squared)
	Deviation in Length & Width	ISO 10545.2	± 0.6 %	Max ± 0.10 %
2	Thickness (Average)	ISO 10545.2	Set by Manufacture	10.4 mm
	Deviation in Thickness	ISO 10545.2	± 10 %	Max ± 2.0 %
3	Straightness of Sides	ISO 10545.2	± 0.5 % (Max 2 mm)	0.2 % (Max) (1.0 mm)
4	Rectangularity	ISO 10545.2	± 0.6 % (Max 4 mm)	Rectified (Diagonal ±0.3mm)
5	Surface Flatness	ISO 10545.2	± 0.5 % (Max 2 mm)	0.2 % (Max) (1.8 mm)
6	Surface Quality	ISO 10545.2	Min 95 %	Min 95 %

PHYSICAL PROPERTIES

7	Water Absorption by mass (Average)	ISO 10545.3	< 0.5 %	0.2 % (Max 0.3 %)
8	Modulus of Rupture	ISO 10545.4	> 35 N/mm ²	> 40.0 N/mm ²
9	Abrasive Resistance (Maximum)	ISO 10545.6	Set by Manufacture	Class IV (2100 revolutions)
10	Moh's Scale Hardness	EN 101	Set by Manufacture	6.0 – 7.0
11	Density	ISO 10545.3	> 2.0 g/cc	> 2.4 g/c
12	Colour Resistance to light	ISO 10545.16	Resistance	Resistance

THERMAL PROPERTIES

13	Thermal Expansion	ISO 10545.8	< 90.0 X 10 ⁻⁷ °C ⁻¹	74.0 X 10 ⁻⁷ °C ⁻¹
14	Moisture Expansion	ISO 10545.10	Nil	Nil
15	Resistance to Thermal Shock	ISO 10545.9	Min 10 Cycle	Resistant
16	Resistance to Crazing	ISO 10545.11	Min 4 Cycle	Resistant
17	Frost Resistance	ISO 10545.12	Resistance	Resistant

CHEMICAL PROPERTIES

18	Chemical Resistance	ISO 10545.13	Resistant	Resistant
19	Resistance to Stains	ISO 10545.14	Min Class III	Class V

RANDOMNESS & DISPLAY OF THE TILES

20	Display of Tiles	At least 2 tiles should be properly displayed to express random effect
----	------------------	--

APPLICATIONS

Product features are with high abrasion resistance and high scratch hardness. As such, it is indicated for flooring semi commercial areas like hotels etc as well as for domestic use (living room, corridors etc). This is not suitable for wet areas (like open veranda etc) since the smooth surface may be slippery.

Prepared by:-	Manager - QA, R & D	Date	1-Oct-17
Revision No.		Date of Revision	