lo	cell	Size	60cm x 30cm	
IDENTIFICATION NAME Product Category			SAN VICENT FULLY VITRIFIED FULL BODY PORCELAIN	
		RC.SAN.000337.CT.0M	San-Ivory	
		RC.SAN.000636.CT.0M	San-Grey	
		F	FEATURES	
	De	scription of the Test	Test Method	
1	Length & Width (A	verage)	ISO 10545.2	R(600 x 300 mm)
2	Rectangularity (Average)		ISO 10545.2	Rectified (Diagonal ±0.3 mm)
3	Thickness (Average)		ISO 10545.2	9.0 ± 0.3mm
4	Surface Flatness (A	verage)		
	Centre Curvature re work size	lated to the diagonal calculated from	ISO 10545.2	±0.2 % (±0.9 mm,±1.4 mm)
	Edge Curvature rela	ted to the corresponding work size	ISO 10545.2	±0.3 % (±0.9 mm,±1.4 mm)
	Warpage related to t size	the diagonal calculated from the work	ISO 10545.2	±0.3 % (±0.9 mm,±1.4 mm)
5	Water Absorption by mass (Average)		ISO 10545.3	less than 0.5%
6	Modulus of Rupture (Minimum)		ISO 10545.4	35.0 N/mm²
7	Deep abrasion		ISO 10545.6	165 mm <sup>3</sup>
8	Surface abrasion (Minimum)		ISO 10545.7	Class III (>750revolution)
9	Resistance to Thermal Shock		ISO 10545.9	Resistant
10	Resistance to Crazing		ISO 10545.11	Resistant
11	Chemical Resistance		ISO 10545.13	Resistant
12	Resistance to Stains		ISO 10545.14	Class V
13	Moh's Scale Hardness			7
14	Display of Tiles			At least 6 tiles should be properly displayed express random effect
1		A	PPLICATIONS	1
		all body porcelain with high scr ce can be done with fresh water		itable for flooring <b>in medium traffic areas</b> als
	Prepared by:	Eng. Prod.	Date	05-05-2015
	Reviewed by:	Manager - QA, R &D	Date	06-05-2015

Date of Revision

01-12-2019

Revision No.

3